



APPLICATION TECHNIQUES



DESCRIPTION

ALCO Resurfacer Cold Process Adhesive is made of quality refined cutback asphalt, fillers and bonders. It assures a rapid, tight bond similar to a blind nail or a lap cement with prepared rolled roofing.

USE

This material is widely used in cold process roofing systems and with many manufactured coated fiberglass felts and base sheets. It is a general purpose lap and placement for sealing laps or mineral surface rolls, smooth surface roofing and base sheets.

ADVANTAGES

- Easy Application
- Ready to use from the container
- Multi-purpose Adhesive
- Brush or Spray Application



Full ALCO Warranty

Ask your sales representative or visit our Web site for complete details.



ALCO Products offer installers a complete line of roof protection products.

Your Second Line of Defense™

800.323.0029 | www.alco-products.com

PREPARATION

Surface to be repaired must be clean, dry and free from oil, grease, dirt, loose coatings or other foreign matter that may impede adhesion.

APPLICATION

When using mineral surface rolls, smooth surface roofing or base sheets, pour Resurfacer directly from the container and spread approximately 1/16" thick, using a soft bristle brush or squeegee.

APPROXIMATE COVERAGE

Spray	60 SF/Gallon
Brush	40 SF/Gallon

SPECIFICATION

ASTM D-4479, Type I

VOC

Not to Exceed: 300 g/L 2.5 Lbs/Gal

FOR OUTDOOR USE ONLY

DO NOT THIN THIS PRODUCT

SECURE COVER WHEN NOT IN USE

PACKAGING

5 Gallon Pail 36/Pallet

LIMITATIONS

- Not for use on wood surfaces
- For professional use only
- Do not use on surfaces previously coated with Coal Tar
- May not be compatible with some one-ply systems. Check with manufacturer of roof system before application.

PROPERTIES

Flash Point (ASTM D-93):	100° F. +
Weight per Gallon (Approximate):	8.1 Lbs
Viscosity @ 77° F (ASTM D-562):	60 - 130 KU
Non-Volatile (Fed Test Method 141):	50% +
Percent of Fillers:	5% - 20%
Percent of Specially Processed Asphalt:	40% +
Percent of Total Solids, by Volume:	58% +

PROPERTIES (continued)

Film Thickness of 1 GAL/100 SF: (less absorption by surface)	1/64"
Drying Time:	2 – 3 Days
Service Temperature, Extended Exposure:	-30° to 150° F.
Resistance to Oils & Solvents:	Poor
Resistance to Sunlight:	Good
Resistance to Chemicals:	Good
Effect of Weathering:	Slight Chalking
Resistance to Water:	
Under Good Drainage Conditions:	Excellent
Under Continuous Submersion:	Not Recommended

FOR FURTHER SAFETY INFORMATION SEE MSDS REGARDING THIS PRODUCT

PRECAUTIONS

Caution Combustible - Contains Petroleum Distillates

Hazard Rating: Health – 1 Fire – 2 Reactivity – 0
(0 = Least; 4 = Extreme)

Respiratory: Use with adequate ventilation. Inhalation of high vapor concentration may cause headaches and/or dizziness. NIOSH/MSHA Respirators required if TLV is exceeded.

Personal Protection: Avoid prolonged or repeated contact with skin, which may cause irritation. Wear chemical resistant gloves. Do not get in eyes; wear protective goggles. Wear protective clothing if needed. Do not take internally.

Fire Protection: Keep away from heat, open flame and any source of ignition.

FIRST AID

Eye Contact – Rinse immediately with water for 15 minutes and seek medical advice.

Skin Contact – Wash thoroughly with soap and water.

Inhalation – Remove individual to fresh air. If breathing is difficult, administer oxygen. If breathing has stopped, give artificial respiration; get medical attention and keep victim warm.

Ingestion – Do not induce vomiting. Get medical attention immediately.

Waste Disposal – Seal container when not in use. Empty containers must be disposed in an approved landfill in accordance with local, state and Federal regulations.

KEEP OUT OF REACH OF CHILDREN!